



01/02/2024

To Whom it may concern,

This material is currently produced at our "Independent" facility (FDOT mine #11-490) this material is shipped and produced utilizing an approved quality control plan. The fine aggregate "Mason Sand" product number (1008) is a washed and graded product. Each load is accompanied by an individual ticket.

### 1008-Mason Sand

| Procedure    | Sieve/Test     | Average | Unit | Mason Sand |
|--------------|----------------|---------|------|------------|
|              | #4 (4.75mm)    | 100     | %    |            |
|              | #8 (2.36mm)    | 100     | %    |            |
|              | #16 (1.18mm)   | 100     | %    |            |
|              | #30 (.6mm)     | 99      | %    |            |
|              | #50 (.3mm)     | 71      | %    |            |
|              | #100 (.15mm)   | 11      | %    |            |
|              | #200 (75µm)    | 0.3     | %    |            |
| AASHTO T-27  | FM             | 1.19    |      |            |
| AASHTO T-255 | Total Moisture | 6.4     | %    | 0.0-6.0    |
|              | D10 (ES)       | 0.1417  | mm   |            |
|              | D50            | 0.24    | mm   |            |
|              | D60            | 0.27    | mm   |            |
|              | Cc             | 0.98    |      |            |
|              | Cu             | 1.92    |      |            |

Sincerely,

Mario Cardenas  
Quality Control Manager  
E.R. Jahna Ind, Inc.  
Office: 352-394-7455  
Cell: 863-528-2335  
Fax: 352-394-8730

Name/Title

David Clements / Mine manager



01/02/2024