




Basic Quality Statistical Summary Report

Plant 1070-Independent South Mine (FDOT Pit#11-298)
Product 1004-Well Point Sand
Specification Well Point
Period 12/23/2023 - 01/23/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	1	99.8			95-100
#8 (2.36mm)	1	98.5			85-100
#16 (1.18mm)	1	86.2			64-97
#30 (.6mm)	1	46.6			19-70
#50 (.3mm)	1	14.0			3-35
#100 (.15mm)	1	1.9			0-7
#200 (75µm)	1	0.05			
Pan	1	0.00			
FM	1	2.529			2.6-2.9
Total Moisture	1	3.311			
D10 (ES)	1	0.24			
D50	1	0.64			
D60	1	0.75			
D15/D85	1	0.27			
Cc	1	0.99			
Cu	1	3.16			



Query

Query Selections
Date Created 01/23/2024
Date Range 12/23/2023 - 01/23/2024
Plant Independent South Mine (FDOT Pit#11-298)
Sample Type Shipping