




Basic Quality Statistical Summary Report

Plant 1050-Independent North Mine (FDOT Pit #11-490)
Product 1001-FDOT Concrete Silica Sand Code F01
Specification FLDOT Silica Sand
Period 01/19/2024 - 01/26/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	1	0		0-5	0-5
#8 (2.36mm)	1	1		0-15	0-15
#16 (1.18mm)	1	11		4-33	3-35
#30 (.6mm)	1	35		32-73	30-75
#50 (.3mm)	1	83		67-93	65-95
#100 (.15mm)	1	99		93-100	93-100
#200 (75µm)	1	100		96-100	96-100
Pan	1	100			
FM	1	2.29		2.08-2.4\2.25	2.05-2.45
Total Moisture	1	2.2			



Query

Query Selections
Date Created 01/26/2024
Date Range 01/19/2024 - 01/26/2024
Plant Independent North Mine (FDOT Pit #11-490)
Sample Type Shipping
Agency Florida DOT MAC