




# Basic Quality Statistical Summary Report

**Plant** 1050-Independent North Mine (FDOT Pit #11-490)  
**Product** 1008-Mason Sand  
**Specification**  
**Period** 01/26/2024 - 02/02/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	4	0	0.0		
#8 (2.36mm)	4	0	0.0		
#16 (1.18mm)	4	0	0.0		
#30 (.6mm)	4	2	1.0		
#50 (.3mm)	4	26	5.2		
#100 (.15mm)	4	84	2.3		
#200 (75µm)	4	99.8	0.06		
Pan	4	100.0	0.00		
FM	4	1.12	0.090		
Total Moisture	4	4.5	1.52		



**Query**

Query Selections

Date Created 02/02/2024

Date Range 01/26/2024 - 02/02/2024

Plant Independent North Mine (FDOT Pit #11-490)-1050

Sample Type Shipping