




Basic Quality Statistical Summary Report

Plant 1030-Haines City Mine (FDOT Pit #16-024)
Product 1009-Concrete Sand
Specification Concrete Sand
Period 01/26/2024 - 02/02/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	5	100.0	0.00	95-100	95-100
#8 (2.36mm)	5	99.9	0.04	85-100	85-100
#16 (1.18mm)	5	96.4	0.33	65-98	65-100
#30 (.6mm)	5	72.1	3.02	25-75	≥25
#50 (.3mm)	5	42.5	0.88	5-44	5-45
#100 (.15mm)	5	7.5	1.07	0-10	0-10
#200 (75µm)	5	0.2	0.09	0-4	0-4
Pan	5	0.0	0.00		
FM	5	1.82	0.038	1.8-2.2\2	
Total Moisture	5	4.2	0.52	0-5	0-6



Query

Query Selections
Date Created 02/02/2024
Date Range 01/26/2024 - 02/02/2024
Plant Haines City Mine (FDOT Pit #16-024)
Sample Type Shipping