




Basic Quality Statistical Summary Report

Plant 2010-Ortona Sand Company (FDOT Pit # 05-045)
Product 1001-FDOT Concrete Silica Sand Code F01
Specification FDOT Concrete Silica Sand Code F01
Period 01/26/2024 - 02/02/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	2	100.0	0.00		95-100
#8 (2.36mm)	2	99.9	0.00		85-100
#16 (1.18mm)	2	95.5	0.42	67-96	65-97
#30 (.6mm)	2	48.9	0.14	27-68	25-70
#50 (.3mm)	2	11.7	0.57		5-35
#100 (.15mm)	2	0.6	0.14		0-7
#200 (75µm)	2	0.0	0.00		
Pan	2	0.0	0.00		
FM	2	2.44	0.007	2.22-2.57/2.4	2.2-2.6
Total Moisture	2	3.0	0.07		



Query

Query Selections
Date Created 02/02/2024
Date Range 01/26/2024 - 02/02/2024
Plant Ortona Sand Company (FDOT Pit # 05-045)
Sample Type Shipping
Agency Florida DOT MAC