




# Basic Quality Statistical Summary Report

**Plant** 1050-Independent North Mine (FDOT Pit #11-490)  
**Product** 1009-Concrete Sand  
**Specification** Concrete Sand  
**Period** 03/29/2024 - 04/05/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	5	100.0	0.00		95-100
#8 (2.36mm)	5	99.8	0.07		85-100
#16 (1.18mm)	5	96.3	1.16	67-98	65-99
#30 (.6mm)	5	74.2	5.92	27-79	25-80
#50 (.3mm)	5	27.3	2.05	7-38	5-40
#100 (.15mm)	5	2.2	1.29	0-6	0-7
#200 (75µm)	5	0.1	0.05		0-4
Pan	5	0.0	0.00		
FM	5	2.00	0.072	1.87-2.18\2	1.85-2.2
Total Moisture	5	3.6	0.53		



**Query**

Query Selections  
Date Created 04/05/2024  
Date Range 03/29/2024 - 04/05/2024  
Plant Independent North Mine (FDOT Pit #11-490)  
Sample Type Shipping