




Basic Quality Statistical Summary Report

Plant 1050-Independent North Mine (FDOT Pit #11-490)
Product 1008-Mason Sand
Specification
Period 03/29/2024 - 04/05/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	5	0	0.0		
#8 (2.36mm)	5	0	0.0		
#16 (1.18mm)	5	0	0.4		
#30 (.6mm)	5	2	0.8		
#50 (.3mm)	5	29	4.9		
#100 (.15mm)	5	89	3.4		
#200 (75µm)	5	99.7	0.11		
Pan	5	100.0	0.00		
FM	5	1.21	0.085		
Total Moisture	5	5.2	1.53		



Query

Query Selections

Date Created 04/05/2024

Date Range 03/29/2024 - 04/05/2024

Plant Independent North Mine (FDOT Pit #11-490)-1050

Sample Type Shipping