




# Basic Quality Statistical Summary Report

**Plant** 1130-Green Bay Mine (FDOT Pit #16-608)  
**Product** 1009-Concrete Sand  
**Specification** Concrete Sand  
**Period** 03/29/2024 - 04/05/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	8	100.0	0.00	95-100	
#8 (2.36mm)	8	100.0	0.05	85-100	
#16 (1.18mm)	8	96.2	0.61	65-97	
#30 (.6mm)	8	70.9	3.74	25-75	
#50 (.3mm)	8	36.1	3.55	5-40	
#100 (.15mm)	8	3.2	0.98	0-7	
#200 (75µm)	8	0.1	0.07		
Pan	8	0.0	0.00		
FM	8	1.94	0.078	1.82-2.18\2	1.8-2.2
Total Moisture	8	4.2	0.94	1-5	1-5



**Query**

Query Selections

Date Created 04/05/2024

Date Range 03/29/2024 - 04/05/2024

Plant Green Bay Mine (FDOT Pit #16-608)

Sample Type Shipping