




# Basic Quality Statistical Summary Report

**Plant** 1130-Green Bay Mine (FDOT Pit #16-608)  
**Product** 1009-Concrete Sand  
**Specification** Concrete Sand  
**Period** 04/17/2024 - 04/24/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	10	100.0	0.00	95-100	
#8 (2.36mm)	10	99.9	0.05	85-100	
#16 (1.18mm)	10	95.7	0.51	65-97	
#30 (.6mm)	10	66.3	1.59	25-75	
#50 (.3mm)	10	31.4	5.05	5-40	
#100 (.15mm)	10	3.0	1.00	0-7	
#200 (75µm)	10	0.2	0.08		
Pan	10	0.0	0.00		
FM	10	2.04	0.067	1.82-2.18\2	1.8-2.2
Grad Loss	10	0.066	0.0846		
Total Moisture	10	3.5	0.81	1-5	1-5
D10 (ES)	10	0.1794	0.00869		
D50	10	0.43	0.026		
D60	10	0.53	0.023		
Cc	10	0.89	0.106		
Cu	10	2.95	0.109		



**Query**

Query Selections

Date Created 04/24/2024

Date Range 04/17/2024 - 04/24/2024

Plant Green Bay Mine (FDOT Pit #16-608)

Sample Type Shipping