




# Basic Quality Statistical Summary Report

**Plant** 1130-Green Bay Mine (FDOT Pit #16-608)  
**Product** 1008-Mason Sand  
**Specification** Mason Sand  
**Period** 04/17/2024 - 04/24/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	3	100	0.0	97-100	
#8 (2.36mm)	3	100	0.0	97-100	
#16 (1.18mm)	3	100	0.0	95-100	
#30 (.6mm)	3	98	0.6	85-100	
#50 (.3mm)	3	87	0.6	35-90	
#100 (.15mm)	3	10	1.5	3-35	
#200 (75µm)	3	0.1	0.15		
Pan	3	0.0	0.00		
FM	3	1.06	0.006	0.9-1.4	1.2
Grad Loss	3	0.058	0.1005		
Total Moisture	3	4.5	0.52	0-5.5	0-6
D10 (ES)	3	0.1483	0.00391		
D50	3	0.22	0.006		
D60	3	0.24	0.006		
Cc	3	0.93	0.010		
Cu	3	1.59	0.042		



**Query**

Query Selections

Date Created 04/24/2024

Date Range 04/17/2024 - 04/24/2024

Plant Green Bay Mine (FDOT Pit #16-608)

Sample Type Shipping