




# Basic Quality Statistical Summary Report

**Plant** 1130-Green Bay Mine (FDOT Pit #16-608)  
**Product** 1004-Well Point Sand  
**Specification** FLDOT Silica Sand  
**Period** 04/17/2024 - 04/24/2024

| Sieve/Test     | Tests | Average | St Dev  | Target | Specification |
|----------------|-------|---------|---------|--------|---------------|
| #4 (4.75mm)    | 3     | 100.0   | 0.00    |        | 95-100        |
| #8 (2.36mm)    | 3     | 99.8    | 0.06    |        | 85-100        |
| #16 (1.18mm)   | 3     | 90.8    | 1.59    |        | 65-97         |
| #30 (.6mm)     | 3     | 33.2    | 2.62    |        | 25-70         |
| #50 (.3mm)     | 3     | 1.6     | 0.23    |        | 5-35          |
| #100 (.15mm)   | 3     | 0.1     | 0.10    |        | 0-7           |
| #200 (75µm)    | 3     | 0.08    | 0.042   |        | 0-4           |
| Pan            | 3     | 0.00    | 0.000   |        |               |
| FM             | 3     | 2.74    | 0.045   | 2.6    | 2.6-2.99      |
| Total Moisture | 3     | 3.7     | 0.85    |        |               |
| D10 (ES)       | 3     | 0.3610  | 0.00637 |        |               |
| D50            | 3     | 0.73    | 0.020   |        |               |
| D60            | 3     | 0.82    | 0.020   |        |               |
| Cu             | 3     | 2.28    | 0.023   |        |               |



**Query**

Query Selections

Date Created 04/24/2024

Date Range 04/17/2024 - 04/24/2024

Plant Green Bay Mine (FDOT Pit #16-608)

Sample Type Shipping