




Basic Quality Statistical Summary Report

Plant 2010-Ortona Sand Company (FDOT Pit # 05-045)
Product 1009-Concrete Sand
Specification Concrete Sand
Period 04/17/2024 - 04/24/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	6	100.0	0.00	95-100	
#8 (2.36mm)	6	99.9	0.04	85-100	
#16 (1.18mm)	6	96.8	0.35	65-99	
#30 (.6mm)	6	56.4	3.30	25-70	
#50 (.3mm)	6	14.9	0.67	5-35	
#100 (.15mm)	6	0.6	0.32	0-7	
#200 (75µm)	6	0.0	0.00		
Pan	6	0.0	0.00		
FM	6	2.31	0.031		
Total Moisture	6	3.2	0.19		
D10 (ES)	6	0.24	0.005		
D50	6	0.54	0.029		
D60	6	0.64	0.030		
D15/D85	6	0.31	0.008		
Cc	6	1.00	0.014		
Cu	6	2.68	0.173		



Query

Query Selections
Date Created 04/24/2024
Date Range 04/17/2024 - 04/24/2024
Plant Ortona Sand Company (FDOT Pit # 05-045)
Sample Type Shipping