




Basic Quality Statistical Summary Report

Plant 2010-Ortona Sand Company (FDOT Pit # 05-045)
Product 1008-Mason Sand
Specification Mason Sand
Period 04/17/2024 - 04/24/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	6	100	0.0	100-100	
#8 (2.36mm)	6	100	0.0	100-100	
#16 (1.18mm)	6	98	0.5	97-100	
#30 (.6mm)	6	75	3.7	80-100	
#50 (.3mm)	6	44	4.8	43-85	
#100 (.15mm)	6	4	3.3	0-25	
#200 (75µm)	6	0.1	0.04		
Pan	6	0.0	0.00		
FM	6	1.78	0.058		
Grad Loss	6	0.000	0.0000		
Total Moisture	6	3.8	0.23	0-5	0-6
D10 (ES)	6	0.16	0.008		
D50	6	0.34	0.026		
D60	6	0.42	0.029		
D15/D85	6	0.23	0.026		
Cu	6	2.58	0.189		



Query

Query Selections
Date Created 04/24/2024
Date Range 04/17/2024 - 04/24/2024
Plant Ortona Sand Company (FDOT Pit # 05-045)
Sample Type Shipping