




Basic Quality Statistical Summary Report

Plant 1210-Liberty Sand Mine
Product 1001-FDOT Concrete Silica Sand Code F01
Specification FLDOT Silica Sand
Period 04/17/2024 - 04/24/2024

| Sieve/Test | Tests | Average | St Dev | Target | Specification |
|-----------------------|-------|---------|--------|---------|---------------|
| #4 (4.75mm) | 11 | 99 | 0.5 | | 95-100 |
| #8 (2.36mm) | 11 | 92 | 0.9 | | 85-100 |
| #16 (1.18mm) | 11 | 72 | 3.0 | | 65-97 |
| #30 (.6mm) | 11 | 44 | 3.7 | | 25-70 |
| #50 (.3mm) | 11 | 23 | 3.4 | | 5-35 |
| #100 (.15mm) | 11 | 5 | 1.1 | | 0-7 |
| #200 (75µm) | 11 | 0.18 | 0.075 | | 0-4 |
| Pan | 11 | 0.00 | 0.000 | | |
| FM | 11 | 2.64 | 0.112 | 2.4-2.8 | 2.4-2.8 |
| -#200 (75um) | 1 | 0.04 | | | |
| Wash Loss (#200/75um) | 1 | 0.04 | | | |
| Total Moisture | 10 | 3.7 | 0.69 | | |
| Color | 1 | 1 | | | |
| D10 (ES) | 11 | 0.18 | 0.013 | | |
| Cu | 11 | 4.87 | 0.139 | | |



Query

Query Selections
Date Created 04/24/2024
Date Range 04/17/2024 - 04/24/2024
Plant Liberty Sand Mine
Sample Type Shipping