




Basic Quality Statistical Summary Report

Plant 1050-Independent North Mine (FDOT Pit #11-490)
Product 1009-Concrete Sand
Specification Concrete Sand
Period 04/17/2024 - 04/24/2024

| Sieve/Test | Tests | Average | St Dev | Target | Specification |
|----------------|-------|---------|---------|-------------|---------------|
| #4 (4.75mm) | 6 | 100.0 | 0.00 | | 95-100 |
| #8 (2.36mm) | 6 | 99.8 | 0.04 | | 85-100 |
| #16 (1.18mm) | 6 | 97.0 | 0.66 | 67-98 | 65-99 |
| #30 (.6mm) | 6 | 79.4 | 2.87 | 27-79 | 25-80 |
| #50 (.3mm) | 6 | 29.1 | 1.68 | 7-38 | 5-40 |
| #100 (.15mm) | 6 | 1.6 | 0.67 | 0-6 | 0-7 |
| #200 (75µm) | 6 | 0.1 | 0.05 | | 0-4 |
| Pan | 6 | 0.0 | 0.00 | | |
| FM | 6 | 1.93 | 0.040 | 1.87-2.18\2 | 1.85-2.2 |
| Total Moisture | 6 | 3.2 | 0.41 | | |
| D10 (ES) | 6 | 0.1856 | 0.00419 | | |
| D50 | 6 | 0.40 | 0.010 | | |
| D60 | 6 | 0.46 | 0.015 | | |
| Cc | 6 | 1.08 | 0.030 | | |
| Cu | 6 | 2.48 | 0.086 | | |



Query

Query Selections
Date Created 04/24/2024
Date Range 04/17/2024 - 04/24/2024
Plant Independent North Mine (FDOT Pit #11-490)
Sample Type Shipping