




Basic Quality Statistical Summary Report

Plant 1050-Independent North Mine (FDOT Pit #11-490)
Product 1008-Mason Sand
Specification Mason Sand
Period 04/17/2024 - 04/24/2024

| Sieve/Test | Tests | Average | St Dev | Target | Specification |
|----------------|-------|---------|---------|---------------|---------------|
| #4 (4.75mm) | 6 | 100 | 0.0 | 97-100 | |
| #8 (2.36mm) | 6 | 100 | 0.0 | 97-100 | |
| #16 (1.18mm) | 6 | 100 | 0.0 | 95-100 | |
| #30 (.6mm) | 6 | 99 | 1.1 | 85-100 | |
| #50 (.3mm) | 6 | 73 | 7.9 | 35-90 | |
| #100 (.15mm) | 6 | 12 | 4.3 | 0-35 | |
| #200 (75µm) | 6 | 0.4 | 0.19 | | |
| Pan | 6 | 0.0 | 0.00 | | |
| FM | 6 | 1.16 | 0.122 | 1.05-1.45\1.2 | |
| Total Moisture | 6 | 5.0 | 0.57 | 0-5 | 0-6 |
| D10 (ES) | 6 | 0.1347 | 0.01813 | | |
| D50 | 6 | 0.23 | 0.019 | | |
| D60 | 6 | 0.26 | 0.020 | | |
| Cc | 6 | 0.99 | 0.094 | | |
| Cu | 6 | 1.94 | 0.111 | | |



Query

Query Selections
Date Created 04/24/2024
Date Range 04/17/2024 - 04/24/2024
Plant Independent North Mine (FDOT Pit #11-490)
Sample Type Shipping