




# Basic Quality Statistical Summary Report

**Plant** 1030-Haines City Mine (FDOT Pit #16-024)  
**Product** 1009-Concrete Sand  
**Specification** Concrete Sand  
**Period** 04/17/2024 - 04/24/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	6	100.0	0.00	95-100	95-100
#8 (2.36mm)	6	99.8	0.08	85-100	85-100
#16 (1.18mm)	6	96.1	1.05	65-98	65-100
#30 (.6mm)	6	67.4	4.73	25-75	≥25
#50 (.3mm)	6	34.8	8.37	5-44	5-45
#100 (.15mm)	6	7.7	3.58	0-10	0-10
#200 (75µm)	6	0.1	0.08	0-4	0-4
Pan	6	0.0	0.00		
FM	6	1.94	0.149	1.8-2.2\2	
Total Moisture	6	2.8	0.86	0-5	0-6
D10 (ES)	6	0.16	0.020		
D50	6	0.41	0.056		
D60	6	0.51	0.058		
Cc	6	0.90	0.124		
Cu	6	3.22	0.328		



**Query**

Query Selections

Date Created 04/24/2024

Date Range 04/17/2024 - 04/24/2024

Plant Haines City Mine (FDOT Pit #16-024)

Sample Type Shipping