




Basic Quality Statistical Summary Report

Plant 1030-Haines City Mine (FDOT Pit #16-024)
Product 1008-Mason Sand
Specification Mason Sand
Period 04/17/2024 - 04/24/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	6	100	0.0	97-100	
#8 (2.36mm)	6	100	0.0	97-100	
#16 (1.18mm)	6	100	0.4	90-100	
#30 (.6mm)	6	95	3.7	65-100	
#50 (.3mm)	6	77	15.5	35-90	
#100 (.15mm)	6	14	4.1	0-40	
#200 (75µm)	6	0.2	0.12		
Pan	6	0.0	0.00		
FM	6	1.14	0.226		
Total Moisture	6	3.4	1.16	0-6\3	0-7
D10 (ES)	6	0.13	0.018		
D50	6	0.23	0.027		
D60	6	0.26	0.034		
Cc	6	1.02	0.118		
Cu	6	2.00	0.129		



Query

Query Selections
Date Created 04/24/2024
Date Range 04/17/2024 - 04/24/2024
Plant Haines City Mine (FDOT Pit #16-024)
Sample Type Shipping