




# Basic Quality Statistical Summary Report

**Plant** 1070-Independent South Mine (FDOT Pit#11-298)  
**Product** 1009-Concrete Sand  
**Specification** Concrete Sand  
**Period** 04/01/2024 - 05/03/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	12	100.0	0.09		95-100
#8 (2.36mm)	12	99.3	0.35		85-100
#16 (1.18mm)	12	93.0	1.97	67-98	65-99
#30 (.6mm)	12	70.8	6.55	27-79	25-80
#50 (.3mm)	12	<b>41.8</b>	6.22	7-38	5-40
#100 (.15mm)	12	<b>7.2</b>	1.74	0-6	0-7
#200 (75µm)	12	0.2	0.14		0-4
Pan	12	0.0	0.00		
FM	12	1.880	0.1524	1.87-2.18\2	1.85-2.2
Total Moisture	12	5.283	1.5093		
D10 (ES)	12	0.16	0.007		
D50	12	0.37	0.055		
D60	12	0.47	0.070		
Cc	12	0.78	0.039		
Cu	12	2.94	0.363		



**Query**

Query Selections  
Date Created 05/03/2024  
Date Range 04/01/2024 - 05/03/2024  
Plant Independent South Mine (FDOT Pit#11-298)  
Sample Type Shipping