




# Basic Quality Statistical Summary Report

**Plant** 1070-Independent South Mine (FDOT Pit#11-298)  
**Product** 1008-Mason Sand  
**Specification** Mason Sand  
**Period** 04/26/2024 - 05/03/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	3	100	0.0	97-100	
#8 (2.36mm)	3	100	0.0	97-100	
#16 (1.18mm)	3	100	0.6	95-100	
#30 (.6mm)	3	95	6.1	85-100	
#50 (.3mm)	3	61	40.4	35-90	
#100 (.15mm)	3	12	10.4	0-35	
#200 (75µm)	3	0.3	0.06		
Pan	3	0.0	0.00		
FM	3	1.325	0.5654	1.05-1.45\1.2	
Total Moisture	3	4.957	0.7352	0-5	0-6
D10 (ES)	3	0.15	0.076		
D50	3	0.28	0.121		
D60	3	0.31	0.133		
Cc	3	1.11	0.031		
Cu	3	2.04	0.161		



**Query**

Query Selections  
Date Created 05/03/2024  
Date Range 04/26/2024 - 05/03/2024  
Plant Independent South Mine (FDOT Pit#11-298)  
Sample Type Shipping