




Basic Quality Statistical Summary Report

Plant 1130-Green Bay Mine (FDOT Pit #16-608)
Product 1009-Concrete Sand
Specification Concrete Sand
Period 04/28/2024 - 05/03/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	10	100.0	0.00	95-100	
#8 (2.36mm)	10	99.9	0.04	85-100	
#16 (1.18mm)	10	95.4	0.92	65-97	
#30 (.6mm)	10	68.9	5.83	25-75	
#50 (.3mm)	10	35.2	5.25	5-40	
#100 (.15mm)	10	3.3	0.98	0-7	
#200 (75µm)	10	0.1	0.11		
Pan	10	0.0	0.00		
FM	10	1.97	0.101	1.82-2.18\2	1.8-2.2
Grad Loss	10	0.027	0.0711		
Total Moisture	10	3.2	1.13	1-5	1-5
D10 (ES)	10	0.1747	0.00786		
D50	10	0.41	0.042		
D60	10	0.50	0.052		
Cc	10	0.84	0.093		
Cu	10	2.88	0.209		



Query

Query Selections

Date Created 05/03/2024

Date Range 04/28/2024 - 05/03/2024

Plant Green Bay Mine (FDOT Pit #16-608)

Sample Type Shipping