




Basic Quality Statistical Summary Report

Plant 1130-Green Bay Mine (FDOT Pit #16-608)
Product 1008-Mason Sand
Specification Mason Sand
Period 04/28/2024 - 05/03/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	1	100		97-100	
#8 (2.36mm)	1	100		97-100	
#16 (1.18mm)	1	100		95-100	
#30 (.6mm)	1	97		85-100	
#50 (.3mm)	1	88		35-90	
#100 (.15mm)	1	10		3-35	
#200 (75µm)	1	0.0			
Pan	1	0.0			
FM	1	1.05		0.9-1.4	1.2
Grad Loss	1	0.000			
D10 (ES)	1	0.1496			
D50	1	0.21			
D60	1	0.23			
Cc	1	0.92			
Cu	1	1.56			



Query

Query Selections

Date Created 05/03/2024

Date Range 04/28/2024 - 05/03/2024

Plant Green Bay Mine (FDOT Pit #16-608)

Sample Type Shipping