




# Basic Quality Statistical Summary Report

**Plant** 1130-Green Bay Mine (FDOT Pit #16-608)  
**Product** 1004-Well Point Sand  
**Specification** FLDOT Silica Sand  
**Period** 04/28/2024 - 05/03/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	1	100.0			95-100
#8 (2.36mm)	1	99.9			85-100
#16 (1.18mm)	1	90.3			65-97
#30 (.6mm)	1	41.2			25-70
#50 (.3mm)	1	4.9			5-35
#100 (.15mm)	1	0.2			0-7
#200 (75µm)	1	0.09			0-4
Pan	1	0.00			
FM	1	2.64		2.6	2.6-2.99
Total Moisture	1	4.3			
D10 (ES)	1	0.3310			
D50	1	0.68			
D60	1	0.78			
Cu	1	2.35			



**Query**

Query Selections

Date Created 05/03/2024

Date Range 04/28/2024 - 05/03/2024

Plant Green Bay Mine (FDOT Pit #16-608)

Sample Type Shipping