




# Basic Quality Statistical Summary Report

**Plant** 1050-Independent North Mine (FDOT Pit #11-490)  
**Product** 1009-Concrete Sand  
**Specification** Concrete Sand  
**Period** 04/26/2024 - 05/03/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	5	100.0	0.00		95-100
#8 (2.36mm)	5	99.7	0.08		85-100
#16 (1.18mm)	5	95.1	1.22	67-98	65-99
#30 (.6mm)	5	71.7	4.24	27-79	25-80
#50 (.3mm)	5	28.9	2.65	7-38	5-40
#100 (.15mm)	5	2.6	0.53	0-6	0-7
#200 (75µm)	5	0.1	0.04		0-4
Pan	5	0.0	0.00		
FM	5	2.02	0.080	1.87-2.18\2	1.85-2.2
Total Moisture	5	3.6	0.27		
D10 (ES)	5	0.1830	0.00523		
D50	5	0.42	0.022		
D60	5	0.50	0.029		
Cc	5	1.02	0.038		
Cu	5	2.72	0.108		



**Query**

Query Selections  
Date Created 05/03/2024  
Date Range 04/26/2024 - 05/03/2024  
Plant Independent North Mine (FDOT Pit #11-490)  
Sample Type Shipping