




Basic Quality Statistical Summary Report

Plant 1050-Independent North Mine (FDOT Pit #11-490)
Product 1008-Mason Sand
Specification Mason Sand
Period 04/26/2024 - 05/03/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	6	100	0.0	97-100	
#8 (2.36mm)	6	100	0.0	97-100	
#16 (1.18mm)	6	100	0.0	95-100	
#30 (.6mm)	6	100	0.5	85-100	
#50 (.3mm)	6	61	9.9	35-90	
#100 (.15mm)	6	4	3.4	0-35	
#200 (75µm)	6	0.1	0.16		
Pan	6	0.0	0.00		
FM	6	1.35	0.123	1.05-1.45\1.2	
Total Moisture	6	1.7	2.02	0-5	0-6
D10 (ES)	6	0.1609	0.00914		
D50	6	0.26	0.033		
D60	6	0.30	0.038		
Cc	6	0.90	0.012		
Cu	6	1.84	0.141		



Query

Query Selections
Date Created 05/03/2024
Date Range 04/26/2024 - 05/03/2024
Plant Independent North Mine (FDOT Pit #11-490)
Sample Type Shipping