




Basic Quality Statistical Summary Report

Plant 2010-Ortona Sand Company (FDOT Pit # 05-045)
Product 1008-Mason Sand
Specification Mason Sand
Period 04/28/2024 - 05/03/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	4	100	0.0	100-100	
#8 (2.36mm)	4	100	0.0	100-100	
#16 (1.18mm)	4	98	0.8	97-100	
#30 (.6mm)	4	71	7.6	80-100	
#50 (.3mm)	4	43	4.2	43-85	
#100 (.15mm)	4	6	3.8	0-25	
#200 (75µm)	4	0.1	0.00		
Pan	4	0.0	0.00		
FM	4	1.82	0.039		
Grad Loss	4	0.000	0.0000		
Total Moisture	4	3.8	0.13	0-5	0-6
D10 (ES)	4	0.16	0.014		
D50	4	0.36	0.017		
D60	4	0.48	0.068		
D15/D85	4	0.21	0.034		
Cu	4	2.98	0.700		



Query

Query Selections
Date Created 05/03/2024
Date Range 04/28/2024 - 05/03/2024
Plant Ortona Sand Company (FDOT Pit # 05-045)
Sample Type Shipping