




# Basic Quality Statistical Summary Report

**Plant** 2010-Ortona Sand Company (FDOT Pit # 05-045)  
**Product** 1004-Well Point Sand  
**Specification** Well Point Sand  
**Period** 04/28/2024 - 05/03/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	4	100	0.0	100-100	
#8 (2.36mm)	4	100	0.0	85-100	
#16 (1.18mm)	4	94	0.0	50-95	
#30 (.6mm)	4	41	4.2	0-55	
#50 (.3mm)	4	8	1.3	0-35	
#100 (.15mm)	4	1	0.0	0-5	
#200 (75µm)	4	0.0	0.00		
Pan	4	0.0	0.00		
FM	4	2.56	0.052		
Grad Loss	1	0.000			
Total Moisture	1	2.6			
D10 (ES)	4	0.31	0.008		
D50	4	0.67	0.030		
D60	4	0.76	0.025		
D15/D85	4	0.33	0.008		
D80/D30	4	2.08	0.103		
Cc	4	0.96	0.073		
Cu	4	2.46	0.028		



**Query**

Query Selections  
Date Created 05/03/2024  
Date Range 04/28/2024 - 05/03/2024  
Plant Ortona Sand Company (FDOT Pit # 05-045)  
Sample Type Shipping