




Basic Quality Statistical Summary Report

Plant 1030-Haines City Mine (FDOT Pit #16-024)
Product 1008-Mason Sand
Specification Mason Sand
Period 04/26/2024 - 05/03/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	6	100	0.0	97-100	
#8 (2.36mm)	6	100	0.0	97-100	
#16 (1.18mm)	6	100	0.0	90-100	
#30 (.6mm)	6	99	1.0	65-100	
#50 (.3mm)	6	78	5.0	35-90	
#100 (.15mm)	6	13	3.2	0-40	
#200 (75µm)	6	0.2	0.15		
Pan	6	0.0	0.00		
FM	6	1.10	0.072		
Total Moisture	6	4.0	1.59	0-6\3	0-7
D10 (ES)	6	0.13	0.014		
D50	6	0.22	0.010		
D60	6	0.25	0.010		
Cc	6	1.01	0.079		
Cu	6	1.92	0.160		



Query

Query Selections

Date Created 05/03/2024

Date Range 04/26/2024 - 05/03/2024

Plant Haines City Mine (FDOT Pit #16-024)

Sample Type Shipping