




Basic Quality Statistical Summary Report

Plant 1050-Independent North Mine (FDOT Pit #11-490)
Product 1008-Mason Sand
Specification Mason Sand
Period 07/19/2024 - 07/26/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	3	100	0.0	97-100	
#8 (2.36mm)	3	100	0.0	97-100	
#16 (1.18mm)	3	100	0.6	95-100	
#30 (.6mm)	3	96	1.2	85-100	
#50 (.3mm)	3	66	1.5	35-90	
#100 (.15mm)	3	10	0.6	0-35	
#200 (75µm)	3	0.2	0.00		
Pan	3	0.0	0.00		
FM	3	1.28	0.031	1.05-1.45	1.2
Total Moisture	3	5.9	1.77	0-5	0-6
D10 (ES)	3	0.1459	0.00125		
D50	3	0.25	0.006		
D60	3	0.28	0.006		
Cc	3	0.90	0.006		
Cu	3	1.90	0.025		



Query

Query Selections
Date Created 07/26/2024
Date Range 07/19/2024 - 07/26/2024
Plant Independent North Mine (FDOT Pit #11-490)
Sample Type Shipping