



07/03/2024

To Whom it may concern,

This material is currently produced at our "Independent" facility (FDOT mine #11-298) this material is shipped and produced utilizing an approved quality control plan. The fine aggregate "Concrete Sand" product number (1009) is a washed and graded product. Each load is accompanied by an individual ticket.

1009-Concrete Sand

Procedure	Sieve/Test	Average	Unit	Concrete Sand
	#4 (4.75mm)	99.9	%	95-100
	#8 (2.36mm)	98.7	%	85-100
	#16 (1.18mm)	91.1	%	65-99
	#30 (.6mm)	67.5	%	25-80
	#50 (.3mm)	32.7	%	5-40
	#100 (.15mm)	3.8	%	0-7
	#200 (75µm)	0.2	%	0-4
ASTM C-136	FM	2.062		1.850-2.200

Sincerely,

Mario Cardenas
Quality Control Manager
E.R. Jahna Ind, Inc.
Office: 863-424-0730 ext. 515
Cell: 863-5570342

Name/Title David Clements / Mine manager