




# Basic Quality Statistical Summary Report

**Plant** 1070-Independent South Mine (FDOT Pit#11-298)  
**Product** 1009-Concrete Sand  
**Specification** Concrete Sand  
**Period** 08/27/2024 - 09/03/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	5	100.0	0.04		95-100
#8 (2.36mm)	5	99.3	0.47		85-100
#16 (1.18mm)	5	93.2	0.65	67-98	65-99
#30 (.6mm)	5	72.3	3.82	27-79	25-80
#50 (.3mm)	5	<b>45.3</b>	5.82	7-38	5-40
#100 (.15mm)	5	<b>7.3</b>	1.48	0-6	0-7
#200 (75µm)	5	0.2	0.08		0-4
Pan	5	0.0	0.00		
FM	5	<b>1.827</b>	0.0968	1.87-2.18\2	1.85-2.2
Total Moisture	5	5.251	1.0908		
D10 (ES)	5	0.16	0.007		
D50	5	0.34	0.044		
D60	5	0.44	0.047		
Cc	5	0.76	0.038		
Cu	5	2.76	0.254		



**Query**

Query Selections  
Date Created 09/03/2024  
Date Range 08/27/2024 - 09/03/2024  
Plant Independent South Mine (FDOT Pit#11-298)  
Sample Type Shipping