




# Basic Quality Statistical Summary Report

**Plant** 1070-Independent South Mine (FDOT Pit#11-298)  
**Product** 1004-Well Point Sand  
**Specification** Well Point  
**Period** 08/27/2024 - 09/03/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	1	99.7			95-100
#8 (2.36mm)	1	97.4			85-100
#16 (1.18mm)	1	86.3			64-97
#30 (.6mm)	1	53.5			19-70
#50 (.3mm)	1	18.2			3-35
#100 (.15mm)	1	3.7			0-7
#200 (75µm)	1	0.18			
Pan	1	0.00			
FM	1	<b>2.412</b>			2.6-2.9
Total Moisture	1	3.193			
D10 (ES)	1	0.20			
D50	1	0.56			
D60	1	0.69			
D15/D85	1	0.22			
Cc	1	1.03			
Cu	1	3.38			



**Query**

Query Selections  
Date Created 09/03/2024  
Date Range 08/27/2024 - 09/03/2024  
Plant Independent South Mine (FDOT Pit#11-298)  
Sample Type Shipping