



08/30/2024

To Whom it may concern,

This material is currently produced at our "Ortona" facility (FDOT mine #05-045) this material is shipped and produced utilizing an approved quality control plan. The fine aggregate "Mason Sand" product number (1008) is a washed and graded product. Each load is accompanied by an individual ticket.

1008-Mason Sand

Procedure	Sieve/Test	Average	Unit	Mason Sand
	#4 (4.75mm)	100	%	
	#8 (2.36mm)	100	%	
	#16 (1.18mm)	98	%	
	#30 (.6mm)	78	%	
	#50 (.3mm)	44	%	
	#100 (.15mm)	4	%	
	#200 (75µm)	0.1	%	
ASTM C-136	FM	1.77		
ASTM C-566	Total Moisture	4.7	%	0.0-6.0
	D50	0.34	mm	
	Cu	2.47		

Sincerely,

Mario Cardenas

Quality Control Manager
E.R. Jahna Ind, Inc.
Office: 352-394-7455
Cell: 863-528-2335
Fax: 352-394-8730

Name/Title Mario Cardenas / Quality Control Manager