




Basic Quality Statistical Summary Report

Plant 1050-Independent North Mine (FDOT Pit #11-490)
Product 1008-Mason Sand
Specification Mason Sand
Period 08/27/2024 - 09/03/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	5	100	0.0	97-100	
#8 (2.36mm)	5	100	0.0	97-100	
#16 (1.18mm)	5	100	0.0	95-100	
#30 (.6mm)	5	97	1.3	85-100	
#50 (.3mm)	5	66	7.5	35-90	
#100 (.15mm)	5	14	2.9	0-35	
#200 (75µm)	5	0.3	0.09		
Pan	5	0.0	0.00		
FM	5	1.23	0.112	1.05-1.45	1.2
Total Moisture	5	5.3	2.53	0-5	0-6
D10 (ES)	5	0.1254	0.01504		
D50	5	0.24	0.019		
D60	5	0.28	0.027		
Cc	5	1.00	0.092		
Cu	5	2.24	0.095		



Query

Query Selections
Date Created 09/03/2024
Date Range 08/27/2024 - 09/03/2024
Plant Independent North Mine (FDOT Pit #11-490)
Sample Type Shipping