




Basic Quality Statistical Summary Report

Plant 2010-Ortona Sand Company (FDOT Pit # 05-045)
Product 1009-Concrete Sand
Specification Concrete Sand
Period 08/27/2024 - 09/03/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	67	100.0	0.00	95-100	
#8 (2.36mm)	67	99.9	0.05	85-100	
#16 (1.18mm)	67	97.0	0.84	65-99	
#30 (.6mm)	67	61.8	4.85	25-70	
#50 (.3mm)	67	20.9	4.37	5-35	
#100 (.15mm)	66	1.7	0.91	0-7	
#200 (75µm)	67	0.0	0.04		
Pan	67	0.0	0.00		
SGN	67	52	3.3		
FM	67	2.18	0.093		
Total Moisture	4	3.6	0.10		
D10 (ES)	67	0.21	0.026		
D25	67	0.32	0.025		
D50	67	0.49	0.036		
D60	67	0.58	0.044		
D75	67	0.77	0.049		
D15/D85	67	0.26	0.028		
Cc	67	1.03	0.092		
Cu	67	2.85	0.270		



Query

Query Selections
Date Created 09/03/2024
Date Range 08/27/2024 - 09/03/2024
Plant Ortona Sand Company (FDOT Pit # 05-045)