




Basic Quality Statistical Summary Report

Plant 2010-Ortona Sand Company (FDOT Pit # 05-045)
Product 1001-FDOT Concrete Silica Sand Code F01
Specification FDOT Concrete Silica Sand Code F01
Period 08/27/2024 - 09/03/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	11	100.0	0.00		95-100
#8 (2.36mm)	11	99.8	0.12		85-100
#16 (1.18mm)	11	94.4	2.28	67-96	65-97
#30 (.6mm)	11	46.0	3.23	27-68	25-70
#50 (.3mm)	11	11.3	2.37		5-35
#100 (.15mm)	11	1.0	0.57		0-7
#200 (75µm)	11	0.0	0.12		
Pan	11	0.0	0.00		
FM	11	2.47	0.045	2.22-2.57/2.4	2.2-2.6
-#200 (75um)	1	0.43			
Grad Loss	11	0.000	0.0000		
Wash Loss (#200/75um)	1	0.36			
Total Moisture	7	3.5	0.22		
D10 (ES)	11	0.28	0.025		
D50	11	0.63	0.028		
D60	11	0.73	0.028		
Cc	11	0.95	0.050		
Cu	11	2.66	0.339		



Query

Query Selections
Date Created 09/03/2024
Date Range 08/27/2024 - 09/03/2024
Plant Ortona Sand Company (FDOT Pit # 05-045)