




Basic Quality Statistical Summary Report

Plant 2010-Ortona Sand Company (FDOT Pit # 05-045)
Product 1008-Mason Sand
Specification Mason Sand
Period 08/27/2024 - 09/03/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	3	100	0.0	100-100	
#8 (2.36mm)	3	100	0.0	100-100	
#16 (1.18mm)	3	98	0.0	97-100	
#30 (.6mm)	3	84	3.0	80-100	
#50 (.3mm)	3	49	9.1	43-85	
#100 (.15mm)	3	4	1.2	0-25	
#200 (75µm)	3	0.1	0.00		
Pan	3	0.0	0.00		
FM	3	1.66	0.078		
Grad Loss	3	0.000	0.0000		
Total Moisture	3	4.8	0.85	0-5	0-6
D10 (ES)	3	0.17	0.006		
D50	3	0.31	0.038		
D60	3	0.36	0.046		
D15/D85	3	0.28	0.040		
Cu	3	2.19	0.225		



Query

Query Selections

Date Created 09/03/2024

Date Range 08/27/2024 - 09/03/2024

Plant Ortona Sand Company (FDOT Pit # 05-045)