




Basic Quality Statistical Summary Report

Plant 1210-Liberty Sand Mine
Product 117-GDOT 10NS Concrete Sand
Specification GADOT 10NS
Period 08/27/2024 - 09/03/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
3/8" (9.5mm)	2	100.00	0.000		
#4 (4.75mm)	4	99.46	0.060		95-100
#8 (2.36mm)	4	92.13	2.189		
#16 (1.18mm)	4	72.18	4.289		45-95
#30 (.6mm)	4	41.32	6.263		
#50 (.3mm)	4	17.27	7.723		5-30
#100 (.15mm)	4	4.28	2.476		0-10
#200 (75µm)	4	0.29	0.166		0-3
Pan	4	0.00	0.000		
FM	4	2.73	0.212	2.4-2.85\2.65	
Grad Loss	4	0.118	0.0996		
Total Moisture	4	5.8	2.28	0-5\4	0-6
Color	1	1			
D10 (ES)	4	0.22	0.073		
D50	4	0.72	0.086		
Cu	4	4.31	0.934		



Query

Query Selections
Date Created 09/03/2024
Date Range 08/27/2024 - 09/03/2024
Plant Liberty Sand Mine
Sample Type Shipping