



# Basic Quality Statistical Summary Report

**Plant** 1130-Green Bay Mine (FDOT Pit #16-608)  
**Product** 1009-Concrete Sand  
**Specification** Concrete Sand  
**Period** 10/24/2024 - 10/31/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	13	100.0	0.00	95-100	
#8 (2.36mm)	13	99.9	0.05	85-100	
#16 (1.18mm)	13	96.5	0.33	65-97	
#30 (.6mm)	13	71.5	2.86	25-75	
#50 (.3mm)	13	36.4	4.83	5-40	
#100 (.15mm)	13	3.1	0.96	0-7	
#200 (75µm)	13	0.4	0.26		
Pan	13	0.0	0.00		
FM	13	1.93	0.082	1.82-2.18\2	1.8-2.2
Grad Loss	13	0.020	0.0318		
Total Moisture	13	3.7	0.79	1-5	1-5
D10 (ES)	13	0.1740	0.00578		
D50	13	0.39	0.031		
D60	13	0.48	0.032		
Cc	13	0.85	0.063		
Cu	13	2.74	0.118		



**Query**

Query Selections

Date Created 10/31/2024

Date Range 10/24/2024 - 10/31/2024

Plant Green Bay Mine (FDOT Pit #16-608)

Sample Type Shipping