




# Basic Quality Statistical Summary Report

**Plant** 1130-Green Bay Mine (FDOT Pit #16-608)  
**Product** 1001-FDOT Concrete Silica Sand Code F01  
**Specification** FLDOT Silica Sand  
**Period** 10/24/2024 - 10/31/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	10	100	0.0	95-100	95-100
#8 (2.36mm)	10	100	0.0	85-100	85-100
#16 (1.18mm)	10	94	1.2	67-96	65-97
#30 (.6mm)	10	60	6.2	27-68	25-70
#50 (.3mm)	10	23	5.8	7-33	5-35
#100 (.15mm)	10	1	1.0	0-6	0-7
#200 (75µm)	10	0	0.3	0-4	0-4
Pan	10	0	0.0		
FM	10	2.21	0.136	2.3	2.1-2.5
-#200 (75um)	1	0.16			
Grad Loss	10	0.050	0.0641		
Wash Loss (#200/75um)	1	0.14			
Total Moisture	9	3.5	0.50		
Color	1	3			1-5
D10 (ES)	10	0.2021	0.01681		
D50	10	0.50	0.056		
D60	10	0.60	0.063		
Cc	10	0.96	0.049		
Cu	10	2.96	0.144		



**Query**

Query Selections

Date Created 10/31/2024

Date Range 10/24/2024 - 10/31/2024

Plant Green Bay Mine (FDOT Pit #16-608)

Sample Type Shipping