




Basic Quality Statistical Summary Report

Plant 1130-Green Bay Mine (FDOT Pit #16-608)
Product 1004-Well Point Sand
Specification FLDOT Silica Sand
Period 10/24/2024 - 10/31/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	5	100.0	0.00		95-100
#8 (2.36mm)	5	99.8	0.07		85-100
#16 (1.18mm)	5	91.9	0.98		65-97
#30 (.6mm)	5	41.0	3.07		25-70
#50 (.3mm)	5	2.2	0.52		5-35
#100 (.15mm)	5	0.3	0.38		0-7
#200 (75µm)	5	0.05	0.041		0-4
Pan	5	0.00	0.000		
FM	5	2.65	0.043	2.6	2.6-2.99
Total Moisture	5	2.3	0.24		
D10 (ES)	5	0.3451	0.00582		
D50	5	0.68	0.022		
D60	5	0.77	0.021		
Cu	5	2.24	0.027		



Query

Query Selections

Date Created 10/31/2024

Date Range 10/24/2024 - 10/31/2024

Plant Green Bay Mine (FDOT Pit #16-608)

Sample Type Shipping