




Basic Quality Statistical Summary Report

Plant 2010-Ortona Sand Company (FDOT Pit # 05-045)
Product 1009-Concrete Sand
Specification Concrete Sand
Period 10/24/2024 - 10/31/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	6	100.0	0.00	95-100	
#8 (2.36mm)	6	99.9	0.04	85-100	
#16 (1.18mm)	6	96.1	0.34	65-99	
#30 (.6mm)	6	53.1	2.11	25-70	
#50 (.3mm)	6	17.8	3.37	5-35	
#100 (.15mm)	6	1.3	0.69	0-7	
#200 (75µm)	6	0.0	0.00		
Pan	6	0.0	0.00		
FM	6	2.32	0.050		
Total Moisture	6	3.4	0.10		
D10 (ES)	6	0.22	0.018		
D50	6	0.56	0.023		
D60	6	0.67	0.020		
D15/D85	6	0.27	0.031		
Cc	6	0.99	0.015		
Cu	6	3.05	0.242		



Query

Query Selections
Date Created 10/31/2024
Date Range 10/24/2024 - 10/31/2024
Plant Ortona Sand Company (FDOT Pit # 05-045)
Sample Type Shipping