




Basic Quality Statistical Summary Report

Plant 2010-Ortona Sand Company (FDOT Pit # 05-045)
Product 1008-Mason Sand
Specification Mason Sand
Period 10/24/2024 - 10/31/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	6	100	0.0	100-100	
#8 (2.36mm)	6	100	0.0	100-100	
#16 (1.18mm)	6	98	0.0	97-100	
#30 (.6mm)	6	83	3.4	80-100	
#50 (.3mm)	6	47	3.3	43-85	
#100 (.15mm)	6	5	2.0	0-25	
#200 (75µm)	6	0.1	0.00		
Pan	6	0.0	0.00		
FM	6	1.68	0.046		
Grad Loss	6	0.000	0.0000		
Total Moisture	6	4.4	0.20	0-5	0-6
D10 (ES)	6	0.17	0.005		
D50	6	0.32	0.018		
D60	6	0.39	0.018		
D15/D85	6	0.27	0.030		
Cu	6	2.38	0.121		



Query

Query Selections
Date Created 10/31/2024
Date Range 10/24/2024 - 10/31/2024
Plant Ortona Sand Company (FDOT Pit # 05-045)
Sample Type Shipping