




# Basic Quality Statistical Summary Report

**Plant** 1050-Independent North Mine (FDOT Pit #11-490)  
**Product** 1009-Concrete Sand  
**Specification** Concrete Sand  
**Period** 11/13/2024 - 11/20/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	7	99.9	0.23		95-100
#8 (2.36mm)	7	99.7	0.14		85-100
#16 (1.18mm)	7	94.4	0.39	67-98	65-99
#30 (.6mm)	7	67.7	0.85	27-79	25-80
#50 (.3mm)	7	23.7	0.88	7-38	5-40
#100 (.15mm)	7	1.0	0.17	0-6	0-7
#200 (75µm)	7	0.1	0.13		0-4
Pan	7	0.0	0.00		
FM	7	2.13	0.015	1.87-2.18\2	1.85-2.2
Total Moisture	7	3.3	0.53		
D10 (ES)	7	0.1974	0.00203		
D50	7	0.45	0.008		
D60	7	0.53	0.007		
Cc	7	1.05	0.008		
Cu	7	2.69	0.023		



**Query**

Query Selections  
Date Created 11/20/2024  
Date Range 11/13/2024 - 11/20/2024  
Plant Independent North Mine (FDOT Pit #11-490)  
Sample Type Shipping