




Basic Quality Statistical Summary Report

Plant 1030-Haines City Mine (FDOT Pit #16-024)
Product 1009-Concrete Sand
Specification Concrete Sand
Period 11/13/2024 - 11/20/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	6	100.0	0.00	95-100	95-100
#8 (2.36mm)	6	99.9	0.09	85-100	85-100
#16 (1.18mm)	6	96.8	0.87	65-98	65-100
#30 (.6mm)	6	74.2	3.72	25-75	≥25
#50 (.3mm)	6	37.6	2.82	5-44	5-45
#100 (.15mm)	6	6.1	1.43	0-10	0-10
#200 (75µm)	6	0.1	0.10	0-4	0-4
Pan	6	0.0	0.00		
FM	6	1.86	0.077	1.8-2.2\2	
Total Moisture	6	3.2	0.53	0-5	0-6
D10 (ES)	6	0.16	0.005		
D50	6	0.38	0.022		
D60	6	0.46	0.030		
Cc	6	0.86	0.034		
Cu	6	2.81	0.154		



Query

Query Selections

Date Created 11/20/2024

Date Range 11/13/2024 - 11/20/2024

Plant Haines City Mine (FDOT Pit #16-024)

Sample Type Shipping