




Basic Quality Statistical Summary Report

Plant 1030-Haines City Mine (FDOT Pit #16-024)
Product 1008-Mason Sand
Specification Mason Sand
Period 11/13/2024 - 11/20/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	6	100	0.0	97-100	
#8 (2.36mm)	6	100	0.0	97-100	
#16 (1.18mm)	6	100	0.5	90-100	
#30 (.6mm)	6	96	2.6	65-100	
#50 (.3mm)	6	80	6.9	35-90	
#100 (.15mm)	6	16	1.8	0-40	
#200 (75µm)	6	0.3	0.12		
Pan	6	0.0	0.00		
FM	6	1.08	0.098		
Total Moisture	6	3.8	3.99	0-6\3	0-7
D10 (ES)	6	0.11	0.005		
D50	6	0.22	0.010		
D60	6	0.24	0.013		
Cc	6	1.10	0.036		
Cu	6	2.13	0.109		



Query

Query Selections

Date Created 11/20/2024

Date Range 11/13/2024 - 11/20/2024

Plant Haines City Mine (FDOT Pit #16-024)

Sample Type Shipping