



01/03/2025

To Whom it may concern,

This material is currently produced at our "Independent" facility (FDOT mine #11-298) this material is shipped and produced utilizing an approved quality control plan. The fine aggregate "**Mason Sand**" product number (1008) is a washed and graded product. Each load is accompanied by an individual ticket.

### 1008-Mason Sand

| Procedure  | Sieve/Test     | Average | Unit | Mason Sand  |
|------------|----------------|---------|------|-------------|
|            | #4 (4.75mm)    | 100     | %    |             |
|            | #8 (2.36mm)    | 100     | %    |             |
|            | #16 (1.18mm)   | 98      | %    |             |
|            | #30 (.6mm)     | 94      | %    |             |
|            | #50 (.3mm)     | 80      | %    |             |
|            | #100 (.15mm)   | 11      | %    |             |
|            | #200 (75µm)    | 0.4     | %    |             |
| ASTM C-136 | FM             | 1.173   |      |             |
| ASTM C-566 | Total Moisture | 7.619   | %    | 0.000-6.000 |
|            | D10 (ES)       | 0.14    | mm   |             |
|            | D50            | 0.23    | mm   |             |
|            | D60            | 0.26    | mm   |             |
|            | Cc             | 0.96    |      |             |
|            | Cu             | 1.84    |      |             |

Sincerely,

*Mario Cardenas*

Quality Control Manager  
E.R. Jahna Ind, Inc.  
Office: 863-424-0730 ext.515  
Cell: 863-557-0342

Name/Title

David Clements / Mine manager