




# Basic Quality Statistical Summary Report

**Plant** 1130-Green Bay Mine (FDOT Pit #16-608)  
**Product** 1008-Mason Sand  
**Specification** Mason Sand  
**Period** 12/23/2024 - 01/03/2025

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	9	100	0.0	97-100	
#8 (2.36mm)	9	100	0.0	97-100	
#16 (1.18mm)	9	99	0.8	95-100	
#30 (.6mm)	9	89	3.3	85-100	
#50 (.3mm)	9	70	5.9	35-90	
#100 (.15mm)	9	8	3.2	3-35	
#200 (75µm)	9	0.1	0.07		
Pan	9	0.0	0.00		
FM	9	1.34	0.108	0.9-1.4	1.2
Grad Loss	9	0.000	0.0000		
Total Moisture	9	3.4	0.66	0-5.5	0-6
D10 (ES)	9	0.1511	0.01321		
D50	9	0.24	0.012		
D60	9	0.27	0.017		
Cc	9	0.91	0.059		
Cu	9	1.80	0.166		



**Query**

Query Selections

Date Created 01/03/2025

Date Range 12/23/2024 - 01/03/2025

Plant Green Bay Mine (FDOT Pit #16-608)

Sample Type Shipping