




Basic Quality Statistical Summary Report

Plant 1130-Green Bay Mine (FDOT Pit #16-608)
Product 1004-Well Point Sand
Specification FLDOT Silica Sand
Period 12/23/2024 - 01/03/2025

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	8	100.0	0.00		95-100
#8 (2.36mm)	8	99.9	0.06		85-100
#16 (1.18mm)	8	92.4	1.00		65-97
#30 (.6mm)	8	41.2	1.48		25-70
#50 (.3mm)	8	3.5	3.87		5-35
#100 (.15mm)	8	0.3	0.27		0-7
#200 (75µm)	8	0.02	0.023		0-4
Pan	7	0.00	0.000		
FM	8	2.63	0.035	2.6	2.55-2.99
Total Moisture	8	3.2	0.37		
D10 (ES)	8	0.3339	0.03000		
D50	8	0.67	0.011		
D60	8	0.77	0.012		
Cu	8	2.33	0.273		



Query

Query Selections

Date Created 01/03/2025

Date Range 12/23/2024 - 01/03/2025

Plant Green Bay Mine (FDOT Pit #16-608)

Sample Type Shipping